DNV-GL

KEMA TYPE TEST CERTIFICATE OF COMPLETE TYPE TESTS

Object Four-core power cable 1173-17

Type AL/XLPE/PVC/SWA/PVC

Rated voltage, U_0/U (U_m) 0,6/1 (1,2) kV Conductor material AL Conductor cross-section 4x95 mm² Insulation material XLPE

Manufacturer National Cables Industry,

Sharjah, United Arab Emirates *)

Client National Cables Industry,

Sharjah, United Arab Emirates

Tested by DNV GL Netherlands B.V.,

Arnhem, the Netherlands

Date of tests 3 April to 3 May 2017

The object, constructed in accordance with the description, drawings and photographs incorporated in this Certificate, has been subjected to the series of proving tests in accordance with the complete type test requirements of

IEC 60502-1 (2009) subclauses 17 and 18

This Certificate has been issued by DNV GL following exclusively the STL Guides.

The results are shown in the record of proving Tests and the oscillograms attached hereto. The values obtained and the general performance are considered to comply with the above standard(s) and to justify the ratings assigned by the manufacturer as listed on page 5.

This Certificate applies only to the object tested. The responsibility for conformity of any object having the same type references as that tested rests with the Manufacturer.

*) as declared by the manufacturer

This Certificate consists of 27 pages in total.

DNV GL Netherlands B.V.

J.P. Fonteijne Executive Vice President

KEMA Laboratories



Laboratories

Arnhem, 27 June 2017

INFORMATION SHEET

1 KEMA Type Test Certificate

A KEMA Type Test Certificate contains a record of a series of (type) tests carried out in accordance with a recognized standard. The equipment tested has fulfilled the requirements of this standard and the relevant ratings assigned by the manufacturer are endorsed by DNV GL. In addition, the test object's technical drawings have been verified and the condition of the test object after the tests is assessed and recorded. The Certificate contains the essential drawings and a description of the equipment tested. A KEMA Type Test Certificate signifies that the object meets all the requirements of the named subclauses of the standard. It can be identified by gold-embossed lettering on the cover and a gold seal on its front sheet.

The Certificate is applicable to the equipment tested only. DNV GL is responsible for the validity and the contents of the Certificate. The responsibility for conformity of any object having the same type references as the one tested rests with the manufacturer.

Detailed rules on types of certification are given in DNV GL's Certification procedure applicable to KEMA Laboratories.

2 KEMA Report of Performance

A KEMA Report of Performance is issued when an object has successfully completed and passed a subset (but not all) of test programmes in accordance with a recognized standard. In addition, the test object's technical drawings have been verified and the condition of the test object after the tests is assessed and recorded. The report is applicable to the equipment tested only. A KEMA Report of Performance signifies that the object meets the requirements of the named subclauses of the standard. It can be identified by silver-embossed lettering on the cover and a silver seal on its front sheet.

The sentence on the front page of a KEMA Report of Performance will state that the tests have been carried out in accordance with The object has complied with the relevant requirements.

3 KEMA Test Report

A KEMA Test Report is issued in all other cases. Reasons for issuing a KEMA Test Report could be:

- Tests were performed according to the client's instructions.
- Tests were performed only partially according to the standard.
- No technical drawings were submitted for verification and/or no assessment of the condition of the test object after the tests was performed.
- The object failed one or more of the performed tests.

The KEMA Test Report can be identified by the grey-embossed lettering on the cover and grey seal on its front sheet.

In case the number of tests, the test procedure and the test parameters are based on a recognized standard and related to the ratings assigned by the manufacturer, the following sentence will appear on the front sheet. The tests have been carried out in accordance with the client's instructions. Test procedure and test parameters were based on If the object does not pass the tests such behaviour will be mentioned on the front sheet. Verification of the drawings (if submitted) and assessment of the condition after the tests is only done on client's request.

When the tests, test procedure and/or test parameters are not in accordance with a recognized standard, the front sheet will state the tests have been carried out in accordance with client's instructions.

4 Official and uncontrolled test documents

The official test documents of DNV GL are issued in bound form. Uncontrolled copies may be provided as loose sheets or as a digital file for convenience of reproduction by the client. The copyright has to be respected at all times.

TABLE OF CONTENTS

1	Identification of the test object	5
1.1	Ratings/characteristics of the object tested	5
1.2	Description of the test object	5
1.3	List of documents	7
2	General information	8
2.1	The tests were witnessed by	8
2.2	The tests were carried out by	8
2.3	Subcontracting	8
2.4	Purpose of test	8
2.5	Measurement uncertainty	8
3	Conductor	9
3.1	Measurement of the resistance of the conductor	g
3.2	Measurement of the number of wires of the conductor	9
4	Electrical type tests	10
4.1	Measurement of insulation resistance at ambient temperature	10
4.2	Measurement of insulation resistance at max. conductor temperature	10
4.3	Voltage test for 4 h	11
5	Non-electrical type tests	12
5.1	Measurement of thickness of insulation	12
5.2	Measurement of thickness of non-metallic sheaths	13
5.3	Tests for determining the mechanical properties of insulation before and after ageing	14
5.4	Tests for determining the mechanical properties of non-metallic sheaths before and after ageing	15
5.5	Additional ageing test on pieces of completed cables	16
5.6	Loss of mass test on PVC sheaths of type ST ₂	17
5.7	Pressure test at high temperature on non-metallic sheaths	18
5.8	Test on PVC insulation and sheaths and halogen free sheaths at low temperatures	19
5.9	Test for resistance of PVC insulation and sheaths to cracking (heat shock test)	20
5.10	Hot set test for XLPE insulation	21
5.11	Water absorption test on insulation	22
5.12	Fire tests	23
5.12.1	Flame spread test on single cables	23
5.13	Shrinkage test for XLPE insulation	24

KEMA I	_aboratories -	4- 1173-17
6	Verification of cable construction	25
7	Drawing	
8	Measurement uncertainties	27

1 IDENTIFICATION OF THE TEST OBJECT

1.1 Ratings/characteristics of the object tested

Rated voltage, U_0/U (U_m) 0,6/1,0 (1,2) kV Rated maximum conductor temperature in normal operation 90 °C Rated conductor cross-section 95 mm²

1.2 Description of the test object

Standard IEC 60502-1

Manufacturer National Cable Industy,

Sharjah, United Arab Emirates

Type AL/XLPE/PVC/SWA/PVC

Manufacturing year 2017

Sampling procedure by the manufacturer

Rated voltage, U_0/U 600/1000 V

No. of cores

Marking on the cable DEWA ELECTRIC CABLE 600/1000 V 4x95 mm²

AL/XLPE/PVC/SWA/PVC, IEC 60502-1 NATIONAL

CABLE INDUSTRY, U.A.E. 2017

Conductor

material aluminium
 cross-section 95 mm²

nominal diameter 10,82 x 15,01 mm type class 2, sector shaped

maximum conductor temperature 90 °C

maximum conductor temperature

in normal operation

Insulation

material XLPE
 nominal thickness 1,1 mm

material designation known in KEMA Laboratories' files

material supplier
 core identification
 Riyadh Cables and Metals
 red / yellow / blue / black

Fillers PP-strings

Binder tape

material PP-tapedimensions 40 x 0,10 mm

-6-**KEMA Laboratories** 1173-17

Inner covering

Extruded type PVC, type ST₂ material 1,2 mm nominal thickness

known in KEMA Laboratories' files material designation

Riyadh Cables and Metals manufacturer of the material

Metallic armour

Galvanized steel wires material 47x2,0 mm

nominal diameter / dimensions Link Middle East material supplier

Oversheath

PVC, type ST₂ material 2,3 mm nominal thickness 43 mm outer diameter of cable known in KEMA Laboratories' files

material designation

Riyadh Cables and Metals material supplier

colour black

Manufacturing details insulation system

Sharjah, United Arab Emirates location of manufacturing

National Cable Industry, United Arab Emirates factory identification of extrusion line

Nextrom LP - 150 manufacturer of the extrusion line

51466988 identification of the production batch

1000 m manufacturing length (where cable sample for testing has been taken

from)

sent to KEMA Laboratories

begin: 136 m, end: 186 m length markings on cable sample

1.3 List of documents

The manufacturer has guaranteed that the object submitted for tests has been manufactured in accordance with the following drawings and/or documents. KEMA Laboratories has verified that these drawings and/or documents adequately represent the object tested. The manufacturer is responsible for the correctness of these drawings and/or documents and the technical data presented.

The following drawings and/or documents have been included in this Certificate:

Drawing no./document no.

Revision

4x95 mm², 0,6/1 kV AL/XLPE/PVC/SWA/PVC Power Cable 02

2 GENERAL INFORMATION

2.1 The tests were witnessed by

Name	Company
Humaid Bakhit Humaid Al Shamsi	Dubai Electricity & Water Authority,
	Dubai, United Arab Emirates
Altaf Ahmed Noor Ahmed	National Cable Industry,
(1 to 3 May 2017)	Sharjah, United Arab Emirates

2.2 The tests were carried out by

Name	Company
Bart Vos	DNV GL Netherlands B.V.,
Eelke Rijpstra	Arnhem, the Netherlands
Frank Rasing	

2.3 Subcontracting

All tests were subcontracted to DNV GL - Energy Advisory, Arnhem, the Netherlands.

2.4 Purpose of test

Purpose of the test was to verify whether the material complies with the specified requirements.

2.5 Measurement uncertainty

A table with measurement uncertainties is enclosed in this Certificate. Unless otherwise stated, the measurement uncertainties of the results presented in this Certificate are as indicated in that table.

3 CONDUCTOR

Standard and date

Standard IEC 60502-1 clause 5

Test date 11 April 2017

3.1 Measurement of the resistance of the conductor

Item	Unit	Requirement	Measured/d	Measured/determined		
			red	yellow	blue	black
Resistance	Ω/km	≤ 0,320	0,318	0,312	0,312	0,314

Result

The object passed the test.

3.2 Measurement of the number of wires of the conductor

Item	Unit	Requirement	Measured/determined			
			red	yellow	blue	black
Number of wires	-	≥ 15	37	37	37	37

Result

4 ELECTRICAL TYPE TESTS

4.1 Measurement of insulation resistance at ambient temperature

Standard and date

Standard IEC 60502-1, clause 17.1

Test date 11 April 2017

Item	Unit	Requirement	Measured/determined			
			red	yellow	blue	black
Volume resistivity, ρ at 20 °C	Ω.cm	-	6,1x10 ¹⁶	5,4x10 ¹⁶	5,0x10 ¹⁶	5,4x10 ¹⁶
Insulation resistance constant, K _i at 20 °C	MΩ.km	-	224293	196476	184979	197947

Result

The test results are for information only.

4.2 Measurement of insulation resistance at max. conductor temperature

Standard and date

Standard IEC 60502-1, clause 17.2

Test date 12 April 2017

Item	Unit	Requirement	Measured/determined			
			red	yellow	blue	black
Volume resistivity, ρ at 90 °C	$\Omega.cm$	≥ 10 ¹²	3,3x10 ¹⁵	1,4x10 ¹⁵	1,2x10 ¹⁵	1,3x10 ¹⁵
Insulation resistance						
constant, K _i						
at 90 °C	$M\Omega$.km	≥ 3,67	12067	4981	4550	4899

Result

4.3 Voltage test for 4 h

Standard and date

Standard IEC 60502-1, clause 17.3

Test date 14 April 2017

Environmental conditions

Temperature 20 \pm 5 °C Temperature of test object 25 °C

Applied voltage	Frequency	Duration	Measured/determined
kV	Hz	h	
2,4	50	4	No breakdown

Requirement

No breakdown of the insulation shall occur.

Result

5 NON-ELECTRICAL TYPE TESTS

5.1 Measurement of thickness of insulation

Standard and date

Standard IEC 60502-1, clause 18.1

Test date 19 April 2017

Thickness	Unit	Requirement	Specified	Measured/	Measured/determined		
				red	yellow	blue	black
Nominal	mm	-	1,1	-	-	-	-
Average	mm	≥ 1,1		1,8	1,9	1,9	2,0
Minimum (t _m)	mm	≥ 0,89		1,55	1,63	1,64	1,65

Result

5.2 Measurement of thickness of non-metallic sheaths

Standard and date

Standard IEC 60502-1, clause 18.2

Test date 19 April 2017

Inner covering

zimer covering							
Thickness	Unit	Requirement	Approximate	Measured/determined			
Nominal	mm	-	1,2	-			
Average	mm	-		1,4			
Minimum (t _m)	mm	≥ 0,76		1,38			

Oversheath

Thickness	Unit	Requirement	Specified	Measured/determined
Nominal	mm	≥ 1,8	2,3	-
Average	mm	-		1,8
Minimum (t _m)	mm	≥ 1,64		1,82

Result

5.3 Tests for determining the mechanical properties of insulation before and after ageing

Standard and date

Standard IEC 60502-1, clause 18.3 Test date 12 April to 2 May 2017

Characteristic test data

Temperature during ageing 135 ± 3 °C

Duration 7 days (12 to 19 April 2017)

Item	Unit	Requirement	Measured	Measured/determined		
			red	yellow	blue	black
Without ageing						
Tensile strength	N/mm²	≥ 12,5	26,7	27,0	24,5	25,4
Elongation	%	≥ 200	571	569	541	560
After ageing						
Tensile strength	N/mm²	-	26,8	24,7	26,1	25,3
Variation with samples without ageing	%	± 25 max.	1	-9	7	0
Elongation	%	-	517	506	499	517
Variation with samples without ageing	%	± 25 max.	-9	-11	-8	-8

Result

5.4 Tests for determining the mechanical properties of non-metallic sheaths before and after ageing

Standard and date

Standard IEC 60502-1, clause 18.4 Test date 13 April to 2 May 2017

Characteristic test data

Temperature during ageing 100 ± 2 °C

Duration 7 days (12 to 19 April 2017)

Inner covering

Item	Unit	Requirement	Measured/determined
Without ageing			
Tensile strength	N/mm²	≥ 12,5	17,4
Elongation	%	≥ 150	235
After ageing			
Tensile strength	N/mm²	≥ 12,5	17,3
Variation with samples without ageing	%	± 25 max.	-1
Elongation	%	≥ 150	217
Variation with samples without ageing	%	± 25 max.	-8

Characteristic test data

Temperature during ageing 100 ± 2 °C

Duration 7 days (12 to 19 April 2017)

Oversheath

Item	Unit	Requirement	Measured/determined
Without ageing			
Tensile strength	N/mm²	≥ 12,5	17,9
Elongation	%	≥ 150	211
After ageing			
Tensile strength	N/mm²	≥ 12,5	17,4
Variation with samples without ageing	%	± 25 max.	-3
Elongation	%	≥ 150	196
Variation with samples without ageing	%	± 25 max.	-7

Result

5.5 Additional ageing test on pieces of completed cables

Standard and date

Standard IEC 60502-1, clause 18.5 Test date 13 April to 2 May 2017

Characteristic test data

Temperature during ageing $100 \pm 2 \,^{\circ}\text{C}$

Duration 7 days (14 to 21 April 2017)

Insulation

Item	Unit	Requirement	Measured/determined			
			red	yellow	blue	black
Tensile strength	N/mm²	-	22,1	23,2	22,3	21,7
Variation with samples without ageing	%	± 25 max.	-17	-14	-9	-15
Elongation	%	-	497	517	483	491
Variation with samples without ageing	%	± 25 max.	-13	-9	-11	-12

Inner covering

Item	Unit	Requirement	Measured/determined
Tensile strength	N/mm²	-	19,8
Variation with samples without ageing	%	± 25 max.	-14
Elongation	%	-	211
Variation with samples without ageing	%	± 25 max.	-10

Oversheath

Oversiteden			
Item	Unit	Requirement	Measured/determined
Tensile strength	N/mm²	-	17,7
Variation with samples without ageing	%	± 25 max.	-2
Elongation	%	-	209
Variation with samples without ageing	%	± 25 max.	-1

Result

5.6 Loss of mass test on PVC sheaths of type ST₂

Standard and date

Standard IEC 60502-1, clause 18.6 Test date 12 to 21 April 2017

Characteristic test data

Temperature during ageing 100 ± 2 °C

Duration 7 days (13 to 20 April 2017)

Inner covering

Item	Unit	Requirement	Measured/Determined
Loss of mass	mg/cm ²	≤ 1,5	0,87

Oversheath

Item	Unit	Requirement	Measured/Determined
Loss of mass	mg/cm ²	≤ 1,5	1,17

Result

5.7 Pressure test at high temperature on non-metallic sheaths

Standard and date

Standard IEC 60502-1, clause 18.7

Test date 26 April 2017

Characteristic test data (inner covering)

Temperature during ageing 90 ± 2 °C Duration 6 h Load 7 N

Inner covering

Item	Unit	Requirement	Measured/Determined
Depth of indentation	%	≤ 50	32

Characteristic test data (oversheath)

Temperature during ageing 90 ± 2 °C Duration 6 h Load 9 N

Oversheath

Item	Unit	Requirement	Measured/Determined
Depth of indentation	%	≤ 50	29

Result

5.8 Test on PVC insulation and sheaths and halogen free sheaths at low temperatures

Standard and date

Standard IEC 60502-1, clause 18.8 Test date 12 to 18 April 2017

Characteristic test data (inner covering)

Temperature -15 ± 2 °C Period of application > 16 h Mass of hammer 1000 g

Inner covering

Item	Unit	Requirement	Measured/Determined
Cold elongation	%	≥ 20	111
Cold impact test	-	No cracks	No cracks

Characteristic test data (oversheath)

Temperature -15 ± 2 °C Period of application > 16 h Mass of hammer 1000 g

Oversheath

Item	Unit	Requirement	Measured/Determined
Cold elongation	%	≥ 20	96
Cold impact test	-	No cracks	No cracks

Result

5.9 Test for resistance of PVC insulation and sheaths to cracking (heat shock test)

Standard and date

Standard IEC 60502-1, clause 18.9

Test date 18 April 2017

Characteristic test data (inner covering)

Temperature 150 ± 3 °C Period of application 1 h Diameter of mandrel 4 mm Number of turns 6 mass

Inner covering

Item	Unit	Requirement	Measured/Determined
Soundness	-	No cracks	No cracks

Characteristic test data (oversheath)

Temperature 150 ± 3 °C Period of application 1 h Diameter of mandrel 4 mm Number of turns 6 mass

Oversheath

Item	Unit	Requirement	Measured/Determined
Soundness	-	No cracks	No cracks

Result

5.10 Hot set test for XLPE insulation

Standard and date

Standard IEC 60502-1, clause 18.11

Test date 19 April 2017

Characteristic test data

Temperature 200 ± 3 °C Time under load 10 min Mechanical stress 20 N/cm²

Item	Unit	Requirement	Measured/determined			
			red	yellow	blue	black
Elongation under load	%	≤ 175	36	35	36	37
Permanent elongation	%	≤ 15	4	3	4	3

Result

5.11 Water absorption test on insulation

Standard and date

Standard IEC 60502-1, clause 18.13 Test date 11 April to 1 May 2017

Characteristic test data

Temperature 85 ± 2 °C Duration 14 days

Item	Unit	Requirement	Measured/determined			
			red	yellow	blue	black
Variation of mass	mg/cm ²	≤ 1	0,05	0,02	0,02	0,02

Result

5.12 Fire tests

5.12.1 Flame spread test on single cables

Standard and date

Standard IEC 60502-1, clause 18.14.1

Test date 12 April 2017

Characteristic test data

Duration 120 s

Item	Unit	Requirement	Measured/determined
Length free of charring	mm	> 50	348
Downward limit charred surface	mm	< 540	503

Result

5.13 Shrinkage test for XLPE insulation

Standard and date

Standard IEC 60502-1, clause 18.16

Test date 24 April 2017

Characteristic test data

Temperature 130 ± 3 °C Duration 1 h

Item	Unit	Requirement	Measured/determined			
			red	yellow	blue	black
Shrinkage	%	≤ 4	2	2	2	2

Result

6 VERIFICATION OF CABLE CONSTRUCTION

Verification of cable construction was carried out in accordance with clauses 5-13 of IEC 60502-1. The results are presented below.

	Observed/determined
Marking on the cable	DEWA ELECTRIC CABLE 600/1000 V 4x95 mm ² AL/XLPE/PVC/SWA/PVC, IEC 60502-1 NATIONAL CABLE INDUSTRY, U.A.E. 2017
Construction	Class 2 Aluminium conductor, sector shaped
	XLPE insulation (red,yellow,blue,black)
	Filler material
	Polypropylene binder tape
	Inner covering, PVC type ST ₂
	Galvanized Steel Wire Armour
	Outer sheath, PVC type ST ₂
Outer diameter of the cable, average	43,0 mm

Result

No significant deviations from the specified requirements are found.

7 DRAWING



<u>Cross Sectional Drawing</u> 4x95 mm², 0.6/1 kV AL/XLPE/PVC/SWA/PVC POWER CABLE

REFERENCE STANDARD: DEWA Specs. 1.5.1.3.5.01-Rev.3 and IEC 60502-1

1. Conductor : Aluminium, Sectoral Stranded Compacted


2. Insulation : Cross-Linked Polyethylene (XLPE)

3. Fillers4. Binding TapePolypropylene StringsPolypropylene Tapes

5. Inner Sheath : Extruded Polyvinyl Chloride (PVC, Type ST2)

6. Armour : Galvanized Steel Wire Armour

7. Outer Sheath : Extruded Polyvinyl Chloride (PVC, Type ST2), Color: BLACK



Size	A1	A2	A3	A4	t1	t2	d3	t4
mm²	mm	mm	mm	mm	mm	mm	mm	mm
4x95	31.1	33.5	37.5	43.0	1.1	1.2	2.0	2.3

A1 = Approx. dia over assembled cores A2 = Approx. diameter over bedding

A3 = Approx. diameter over armour

A4 = Approx. overall diameter

t1 = Nominal thickness of insulation

t2 = Nominal thickness of bedding

d3 = Nominal diameter of armour wire

t4 = Nominal thickness of outer sheath

Color Code: Red, Yellow, Blue & Black

Embossing on the Outer Sheath in Max 150 mm spacing along TWO lines:

DEWA ELECTRIC CABLE 600/1000 V, 4x95 SQMM, AL/XLPE/PVC/SWA/PVC, IEC 60502-1 NATIONAL CABLES INDUSTRY, UAE, 2017

P.O. Box: 27472 Sharjah, U.A.E.

☐ Tel: 06-5311888 ☐ Fax: 06-5311577

E-mail: n_c_i@emirates.net.ae Website: www.nci.ae















FORM # TE01/F06 Rev. 02

8 MEASUREMENT UNCERTAINTIES

The measurement uncertainties in the results presented are as specified below unless otherwise indicated.

Measurement	Measurement uncertainty
Tensile strength test	1%
Measurement of dimensions	5 μm
Measurement loss of mass	0,11 mg : 8,0 gr
Measurement of conductor resistance	0,03% of measured value
Measurement at low temperature	0,1 °c
Measurement in heating cabinets	0,1 °c
Voltage test	2.10 ⁻³ .u + 20v 2.10 ⁻³ .i + 0,2%