

BRE Global Test Report

Fire Testing of National Cables Industry 'New Approval of Single Core' Cables

Prepared for: National Cables Industry

Date: 22 March 2018

Report Number: P106809-1001 Issue: 2

BRE Global Ltd Watford, Herts WD25 9XX

Customer Services 0333 321 8811

From outside the UK: T + 44 (0) 1923 664000 F + 44 (0) 1923 664010 E enquiries@bre.co.uk www.bre.co.uk Prepared for: National Cables Industry Plot No. 06 Al Sajja Industrial Estate Al Dhaid Road Sharjah United Arab Emirates





Prepared by

Name Jenny Morris

Position Cables Testing Manager

Signature



Authorised by

Name Stephen Howard

Position Director of Fire Testing and Certification

Signature

This report is made on behalf of BRE Global and may only be distributed in its entirety, without amendment, and with attribution to BRE Global Ltd to the extent permitted by the terms and conditions of the contract. Test results relate only to the specimens tested. BRE Global has no responsibility for the design, materials, workmanship or performance of the product or specimens tested. This report does not constitute an approval, certification or endorsement of the product tested and no such claims should be made on websites, marketing materials, etc. Any reference to the results contained in this report should be accompanied by a copy of the full report, or a link to a copy of the full report.

BRE Global's liability in respect of this report and reliance thereupon shall be as per the terms and conditions of contract with the client and BRE Global shall have no liability to third parties to the extent permitted in law.

Opinions and interpretations expressed herein are outside the scope of UKAS Accreditation.

Page 2 of 9



Table of Contents 1 Introduction 3 2 **Cable Details** 4 3 **Test results** 6 3.1 BS 6387:2013 - Fire resistance 6 3.1.1 BS 6387:2013 - Resistance to fire alone 6 3.1.2 BS 6387:2013 - Resistance to fire with water 6 3.1.3 BS 6387:2013 - Resistance to fire with mechanical shock 7 3.2 EN 61034-2:2005 - Smoke emission 7 3.3 IEC 60331-21:1999 - Fire resistance 8 3.4 EN 60754-1:2014 - Acid gas emission 8 References 9



1 Introduction

The requirement of the work was to determine the performance of a cable when tested to BS 6387:2013 CWZ [1], EN 61034-2:2005 [2], IEC 60331-21:1999 [3] and EN 60754-1:2014 [4].

The work was undertaken on behalf of the LPCB, Schedule P106809-1000 V2.

This report is issue 2 of BRE report P106809-1001 Issue 1 dated 20 December 2017. LPCB required to carry out additional testing at a higher voltage 1000V on BS 6387 Category C & Z test was added to this report. BRE report P106809-1001 Issue 1 dated 20 December 2017 has been withdrawn with effect from the date of this report.



2 Cable Details

The 1×1.5 mm² cable (BRE sample reference F1231) was a 3.98mm cable diameter which comprised the following components:

- Copper Conductor Stranded
- Mica Tape
- Insulation Green and Yellow

The 1×1.5mm² cable (BRE sample reference F1231) sheath had the following printed marking:

ELECTRIC CABLE 1×1.5 mm² CU/LSZH-FP 450/750 V BS 8592 2017 NATIONAL CABLES INDUSTRY UAE

The $1\times95\text{mm}^2$ cable (BRE sample reference F1504) was a 16.42mm cable diameter which comprised the following components:

- Copper Conductor Stranded
- Mica Tape
- Insulation Green & Yellow

The 1×95mm² cable (BRE sample reference F1504) sheath had the following printed marking:

ELECTRIC CABLE, $1\times95\text{MM}^2$, CU/LSZH-FP, 450/750V, GEN. TO BS EN 50525-3-41 & IEC 60331, 2017, NATIONAL CABLES INDUSTRY, U.A.E.



The 1×400 mm² cable (BRE sample reference F1503) was a 29.83mm cable diameter which comprised the following components:

- Copper Conductor Stranded
- Mica Tape
- Insulation Green & Yellow

The 1×400mm² cable (BRE sample reference F1503) sheath had the following printed marking:

ELECTRIC CABLE, $1\times400\text{MM}^2$, CU/LSZH-FP, 450/750V, GEN. TO BS EN 50525-3-41 & IEC 60331, 2017, NATIONAL CABLES INDUSTRY, U.A.E.

The test specimens were supplied by the client and received on the 5 March 2017 and 28 September 2017. BRE Global was not involved in the sample selection process and therefore cannot comment upon the relationship between samples supplied for test and the product supplied to market.



3 Test results

3.1 BS 6387:2013 - Fire resistance

3.1.1 BS 6387:2013 - Resistance to fire alone

Cable type	BRE sample reference	Test category	Test voltage (Uo/U)	Comment	Result
1×1.5mm²	F1231	С	600/1000V	No fuses ruptured or lamps extinguished	Pass*
1×95mm²	F1504	С	600V	No fuses ruptured or lamps extinguished	Pass**
1×400mm²	F1503	С	600V	No fuses ruptured or lamps extinguished	Pass**
1×400mm²	F1503	С	1000V	No fuses ruptured or lamps extinguished	Pass**

^{* 3} cables tested in a 20mm Stainless Steel conduit

3.1.2 BS 6387:2013 - Resistance to fire with water

Cable type	BRE sample reference	Test category	Test voltage (Uo/U)	Comment	Result
1×1.5mm²	F1231	W	600/1000V	No fuses ruptured or lamps extinguished	Pass*
1×95mm²	F1504	W	600V	No fuses ruptured or lamps extinguished	Pass**

^{* 3} cables tested in a 20mm Stainless Steel conduit

^{** 1} cable tested in a 38mm Stainless Steel Conduit

^{** 1} cable tested in a 20mm Stainless Steel conduit



3.1.3 BS 6387:2013 - Resistance to fire with mechanical shock

Cable type	BRE sample reference	Test category	Test voltage (Uo/U)	Comment	Result
1×1.5mm²	F1231	Z	600/1000V	No fuses ruptured or lamps extinguished	Pass*
1×95mm²	F1504	Z	600V	No fuses ruptured or lamps extinguished	Pass**
1×95mm²	F1504	Z	1000V	No fuses ruptured or lamps extinguished	Pass**

^{* 3} cables tested in a 20mm Stainless Steel conduit

3.2 EN 61034-2:2005 - Smoke emission

Cable Type	BRE sample reference	Cable Diameter (mm)	No. of cable lengths	Minimum light transmission %	Result
1×1.5mm²	F1231	3.98	3 bundles of 7 (21 cables)	84.29	Pass
1×95mm²	F1504	16.42	3 cables	87.66	Pass
1×400mm²	F1503	29.83	2 cables	85.26	Pass

^{** 1} cable tested in a 20mm Stainless Steel conduit



3.3 IEC 60331-21:1999 - Fire resistance

Cable type	Burner Temperature	Test voltage (Uo/U)	Test Duration	Comment	Result
1×1.5mm² F1231	972.0°C	600V	90+15mins	No fuses ruptured or lamps extinguished	Pass
1×95mm² F1504	786.7°C	600V	90+15mins	No fuses ruptured or lamps extinguished	Pass
1×400mm² F1503	786.7°C	600V	90+15mins	No fuses ruptured or lamps extinguished	Pass

3.4 EN 60754-1:2014 - Acid gas emission

Cable	Component	%HCl per gram of sample	
1×1.5mm²	Insulation	-O F0/	
F1231	Mica Tape	<0.5%	



4 References

- 1. BS 6387:2013. Test method for resistance to fire of cables required to maintain circuit integrity under fire conditions. British Standards Institution, London, 2013.
- EN 61034-2:2005, 'Measurement of smoke density of cables burning under defined conditions Part 2: – Test procedure and requirements', International Electrotechnical Commission, Geneva 2005.
- 3. IEC 60331-21:1999. Tests for electric cables under fire conditions Circuit integrity Part 21: Procedures and requirements Cables of rated voltage up to and including 0,6/1,0 kV. International Electrotechnical Commission, Geneva, Switzerland, 1999.
- 4. EN 60754-1:2014, 'Test on gases evolved during combustion of material from cables. Part 1: Determination of the amount of halogen acid gases', International Electrotechnical Commission, Geneva, 2014.

Commercial in Confidence © BRE Global Ltd 2017 Page 9 of 9